

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

| Client : Preference Floors | | | st Number | : | 18-002923 |
|----------------------------|------------|--|-----------|---|------------|
| 19-21 Lanyon Street | | | ue Date | : | 20/06/2018 |
| Dandenong VIC 3175 | | | nt Date | : | 8/08/2018 |
| Sample D | escription | Clients Ref : "AC5 Laminate" Engineered Flooring with laminate wear layer Colour : Dk Brown Nominal Composition : HDF/Laminate wear layer | | | |

Nominal Thickness : 14mm

Nominal Mass per Unit Area/Density :

AS/ISO 9239.1-2003 Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a **Radiant Heat Source**

| Date of Sample Arrival Date Tested | | | | | |
|---------------------------------------|-----------------|-------------|---------------|----------------|----------------|
| CHF Value Length Width | 1 ≥11 ≥11 | 2 ≥11 | 3 ≥11 - | Mean - - | kW/m² kW/m² |
| Smoke Value Length Width | 1 4 <4 | 2 5 - | 3 <4 | Mean - | %.min %.min |

Approx. 12.8kg/m2

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

| - | 138378 | 28043 | | | | Page 1 of 1 |
|----|--|-------|--|---|---|--------------------------------|
| © | Australian Wool testing Authority Ltd Copyright - All Rights Reserved | | NATA | Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing | : Accreditation No. : Accreditation No. : Accreditation No. | 983 985 1356 |
| | | | Ltd makes no warra relate only to the sa be rendered void if | Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by | | |
| | | | the Managing Direc | | ······································ | Machin |
| 02 | 04/11/06 | | | | | MICHAEL A. JACKSON B.Sc.(Hons) |

APPROVED SIGNATORY